

Shanghai SECCO Petrochemical Co., Ltd.

Contact address: 30F, A Building, Far East International Plaza

No.319, Xian Xia Road, Shanghai 200051 P.R. China

Tel: (021) 52574688-3333 (customer service) Fax: (021) 62783737 (customer service)

Email: <u>customerservice@secco.com.cn</u> Website: <u>http://www.secco.com.cn</u>

07/2020

## **SECCO GPPS152**

# **General Purpose Polystyrene Resin**

### **Product description**

*GPPS152* has the characteristics of high transparency, good melt flowability, easy mold relase and good heat resistance, it can balance processability and mechanical properties. The base color of *GPPS152* is near white.

#### **Products applications**

Refrigerator interior parts, fruit and vegetable boxes, cosmetics box, etc.

#### **Product characteristics**

**Typical properties** 

Properties	Test method	Test condition	Units	Typical values
Melt flow rate	GB/T 3682.1	200°C/5kg	g/10min	3.8
Tensile stress at break	GB/T 1040.2	50mm/min	MPa	53
Nominal tensile strain at break	GB/T 1040.2	50mm/min	%	2
Flexural modulus	GB/T 9341	2mm/min	MPa	3100
Flexural strength	GB/T 9341	2mm/min	MPa	88
Charpy unnoteched impact strength	GB/T 1043.1	23°C/1eU	kJ/m²	10
Vicat softening temperature	GB/T 1633	B <sub>50</sub>	${\mathbb C}$	99
Heat distortion temperature	GB/T 1634.2	0.45Mpa	$^{\circ}$	92
Density	ISO1183-1		kg/ m³	1040
Transmissivity	GB/T 2410		%	90
Water absorption	ISO62		%	<0.1
UL flammability	UL 94		Class	94HB
Mold shrinkage	GB/T 17037.4		%	0.3-0.4

<sup>1)</sup> Values given are typical and should not be interpreted as specification.

#### **Additional information**

#### **Product safety compliance**

**GPPS152** complies with the National Food Safety Standard GB 4806.6-2016 for plastic resin used in food-contact parts, FDA regulation CFR 177.1640(c) (1) and the ROHS Directive: Amending Delegated Directive(EU)2015/863 to Directive 2011/65/EU Annex II. **GPPS152** has obtained the UL certificate of the USA. However, the customer is still responsible for determining whether the fabricated product is in compliance with applicable laws and regulations.

#### Safety and material handling

SECCO polystyrene resin has a very low degree of toxicity under normal conditions of use. Please contact your SECCO representative or the local suppliers for more detailed information and/or Material Safety Data Sheet (MSDS) for the specific grade of interest.

Typical application of GPPS152 is injection molding. It is suggested that the injection temperature should be set at 180°C-240°C, and mould temperature at 30-60°C.